
SUNTUF[®] Rooflights Technical Guide Profile: BH (Iron 76/18)





Profile Dimensions

Profile	Thickness	Length	Overall width	Cover Width	Side-Lap
(mm)	(mm)	(m)	(mm)	(mm)	(%)
76 / 18	2.8	1.5 - 7	1045	988	

Load / Span Data

Load	Maximum Roof Span (mm)	Maximum Wall Span (mm)	
(kg/m²)	2.8 mm	2.8 mm	
50	1400	1540	
75	1300	1430	
100	1200	1320	
125	1175	1295	
150	1150	1265	
175	1125	1240	
200	1100	1210	


- The specified dimensions do not supersede the requirements of local construction codes.
- The given spans are according to deflections criterion of L/20, and minimum slope of 10%.
- The maximum roof spans are based on calculation model and practical testing.
- The mentioned load refers to wind and snow load only.
- For vertical application spans can be increased by 10%.

Panel Length

- Maximum recommended panel length 7.0 m.
- Recommended longitude overlaps of 200mm above purlin.
- Each panel to extend 100mm over the fixings line on the purlin.
- Butyl sealing tape **must** be used so seal the gap between the sheets.
- Panels should overhang Min. 50mm and Max. 150mm beyond the last fixings line.

Curved roof

Minimum curving radius 7.0 m.





SUNTUF[®] Rooflights Technical Guide Profile: BH (Iron 76/18)

Positioning

- Make sure the UV protected side faces out.
- Apply one corrugation side-lap. Two corrugations side-lap is recommended for low roof slope and/or high wind areas.
- Side-lap of SUNTUF panels should be installed against the primary direction of rain.
- The SUNTUF panels should be located and installed without any stresses.
 Do not pull, stretch or force the sheets when the profiles are not perfectly matched.
- SUNTUF sheets should overhang Min. 50mm and Max. 150mm beyond the last fixings line.


Sealing - Recommended

- Apply sealing tape over the SUNTUF panel side-lap corrugation crests, where covered by the next panel.
- Apply sealing tape along the bottom and top End-lap (if there is), 2 cm down slope screws centerline or two tapes on both sides of screw centerline.

Fastening

- Pre-drill 10mm holes at crests where screws are positioned.
- Start fastening the screws from the first side-lap (left) through the pre-drilled holes.
- Start fastening the screws on the lower edge purlin (End-lap), through every other corrugation crest (1).
- Fasten screws at the internal purlins, through every third corrugation crest, starting at the same side (2).
- Fasten screws at the upper edge purlin, through every other corrugation crest (1).
- Do not over-tighten!

Fastening Location-for Wall and Roof installation



Screws and Washers Specification

- Crest fixing: Self-drilling 6.5mm (¼") x 50mm (2") screw with 19/25mm diameter- galvanized / Aluminum / stainless metal washer attached to EPDM rubber gasket of 55 to 65 shore hardness.
- In areas with strong winds, when roof slope is low use storm washer with EPDM gasket.














SUNTUF[®] Rooflights Technical Guide Profile: BH (Iron 76/18)



Important Notes

- Use only PALRAM approved accessories, including EPDM rubber washers, silicones, sealing tape, closure fixtures etc.
- For clear SUNTUF onto wooden purlins, apply white acrylic paint, or aluminum tape, in order to prevent over-heating of the purlins.

Cutting Tips

- Use jigsaw or circular saw with fine tooth blades.
- Apply high blade speed with moderate feeding rate.
- Support the sheets near the cutting line.
- Clean the dust and cutting chips after cutting.

Fastening Tips

- Use adjustable electric screwdriver.
- The screw must be installed perpendicular to the SUNTUF sheet.
- Important: Do not over-tighten.

Safety


- Do not step directly on the panel.
- Use stepping boards.
- Work according to local safety regulations.

Handling and Storage

- Store in a dry shaded place, protect from direct sunlight and rain.
- Avoid covering the sheets with heat absorbing materials.
- Avoid contact or environment of chemicals.
- Protect the sheets from any physical damage.











Inasmuch as PALRAM Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any PALRAM Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. PALRAM Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local PALRAM Industries supplier to ensure that you have obtained the most up to date information.